

**TECHNICAL
SHEET**

PROTECT 25

**PROTECT 25
INORGANIC COATING**

DESCRIPTION

PROTECT 25 is an inorganic coating based on chemical bonding Si-O which dries and hardens by the relationship, with the humidity of the air. It is an inorganic paint, has very good grip in several surfaces without any prior priming. It is mono-component so that increases the rentabilidd of the work.



APPLICATIONS

- Application: interior and exterior.
- Wood, metal work, iron, inox, galvanized iron, aluminum, concrete, vinyl, ceramic, granite, marble, plastic, etc.

PROPIEDADES

- Does not quarter
- Does not form blisters
- Is no need to sand to repaint
- Once dry toilet
- Breathable
- Reapplicable
- Non graffiti
- Non stickers
- Self cleaning
- Non pollute

FEATURES

- | | |
|-------------------------------------|----------------------------|
| ▪ Finished: | Matte or Gloss |
| ▪ Performance approximated by hand: | 30 grams m2 |
| ▪ Dry to the touch | (20 Cº HR:60 %) 30 minutes |
| ▪ Total dry : | 24 hours |
| ▪ Total hardening: | 5 days |
| ▪ Colours: | Transparent |

PREPARATION OF THE SURFACE

- The support has to be exempt of strange products, oxides or residues.
- Apply on surfaces well desengrasadas, powder-free and dry.
- If it was cleaned with pressurized water expected to be dry.
- If he was cleaned with chemicals restore PH between 6-8.

INSTRUCTIONS FOR USE

- Do not apply the product with high temperatures.
- Do not apply with humidities above 85%, or at temperatures below 5 ° C or above 35 ° C.
- You can apply to brush, roller aerografica pistol.

GENERAL INFORMATION

- The data outlined here are based on our current knowledge, testing laboratory and in specific circumstances and objective judgments obtained in the practical use.
- Due to the impossibility of establishing an appropriate to each nature and State description, taking into account the surface to protect, it is impossible to ensure total reproducibility in each case.

PRESENTATION

- 4 kg, 1kg, 500gr.

EXPIRATION

- Recommended storage no more than 12 months, taking into account the date of manufacture defined in the original container.
- Keep always the packaging original, perfectly closed and covered.
- Temperature of storage between 15-20 ° C.