

TECHNICAL SHEET

SL100

SL100
PRIMER HLG SYSTEM

DESCRIPTION

SL100 Primer of HLG System.

Acrylic resin with silicone bi components hardens reacting with the H₂O in the air.



APPLICATIONS

- Application: indoor and outdoor.
- Wood, metal work, iron, stainless steel, aluminium, concrete, vinyl, ceramic, granite, marble, plastic, etc.

PROPERTIES

- Improves resistance to weathering, oxidation and adhesion to the base.
- Excellent resistance to chemical products.
- Its use is recommended is surfaces with difficult adherence, as bridge Union to enamels.
- It does not quarter.
- Does not form blisters.
- No need sanding for repainting.
- Once dry toilet.
- Breathable.
- No contaminates.

FEATURES

- | | |
|-------------------------------------|----------------------------------|
| ▪ Finished: | Gloss |
| ▪ Viscosity: | 9,0-12,0s/HIS NK-2 |
| ▪ performance approximated by hand: | 50 grams m ² |
| ▪ Dry to touch: | (20 C° HR:60 %) 5-8 minutes |
| ▪ Repainting: | (20 C° HR: 60 %) 4 hours |
| ▪ Colours: | Transparent , colours letter RAL |
| ▪ Duration of the mixture: | 10 hours a 20 C° |
| ▪ The ratio by weight: | 6-1 |
| ▪ Thinner: | Specific to the 80 % |

PREPARATION OF THE SURFACE

- The support has to be exempt of strange products, oxides or residues.
- Apply on surfaces well desengrasadas, powder-free and dry.
- If it was cleaned with pressurized water expected to be dry.
- If he was cleaned with chemicals restore PH between 6-8.

USE

- Use tables of mixtures.
- The mixture must always do with a digital balance weight.
- Respect the exact proportions detailed in the table of mixtures.
- Do not apply the product with high temperatures.
- Do not apply with humidities above 85%, or at temperatures below 5 ° C or above 35 ° C.
- You can apply brush, roller and gun announce.

GENERAL INFORMATION

- The data outlined here are based on our current knowledge, testing laboratory and in specific circumstances and objective judgments obtained in the practical use.
- Due to the impossibility of establishing an appropriate to each nature and State description, taking into account the surface to protect, it is impossible to ensure total reproducibility in each case.

PRESENTATION:

- Varied.

EXPIRATION:

- Recommended storage no more than 12 months, taking into account the date of manufacture defined in the original container.
- Keep always the packaging original, perfectly closed and covered.
- Temperature of storage between 15-20 ° C.

