

# SG

The natural latex base provides excellent dielectric properties. The greater the glove thickness, the higher its electrical resistance. The ergonomic design enhances comfort, offering superior softness and flexibility, and makes both donning and removal easier.

Insulating gloves are considered one of the most important items of personal protective equipment for electrical work. They form the first line of defence against contact with live components or energised conductors.



**The natural latex glove is available in beige.**

Ref.	Class	Thickness (mm)		Size	Length (mm)	Categories	Working voltage (V) max.	Proof test voltage (V) max.	Withstand voltage (V) max.
		max.	medium						
SG-25 T9 SG-25 T10	00	< 1.1	0.6	7*	360	AZC	500 V AC	2.500 V AC	5.000 V AC
SG-50 T9 SG-50 T10	0	< 1.6	1.0						
SG-10 T9 SG-10 T10	1	< 2.1	1.6	8*	280 - 360 410 - 460	RC	7.500 V AC	10.000 V AC	20.000 V AC
SG-20 T9 SG-20 T10	2	< 2.9	2.3	9					
SG-30 T9 SG-30 T10	3	< 3.5	2.9	10	360	RC	17.000 V AC	20.000 V AC	30.000 V AC
SG-30 T9 SG-30 T10	3	< 3.5	2.9	11					
SG-30 T11 SG-40 T10 SG-40 T11	4	< 4.2	3.8	12*	410	RC	36.000 V AC	40.000 V AC	50.000 V AC

Meaning of letters in 'Categories': A: Acid / Z: Ozone / H: Oil / C: Very low temperature / R: A+Z+H resistance.  
 \* For sizes 7, 8 and 12 consult.

**USE:** Recommended for work in electricity generation, transmission, transformation, and distribution, as well as in the railway, telecommunications, construction, industrial maintenance, photovoltaic panel, and hybrid vehicle battery sectors, among others.

**RECOMMENDATIONS:** Depending on the task, it is advisable to use the insulating latex gloves together with appropriate leather over-gloves to provide additional mechanical protection against abrasion, cutting, tearing, and punctures.

### MECHANICAL AND THERMAL REQUIREMENTS

- Average tensile strength:  $\geq 16$  MPa
- Average elongation at break:  $\geq 600\%$
- Puncture resistance:  $\geq 18$  N/mm
- Tension set:  $\leq 15\%$
- Resistance to very low temperatures: Gloves conditioned for 24 hours at  $-40\text{ }^{\circ}\text{C} \pm 3\text{ }^{\circ}\text{C}$ .
- Flame-retardant test: Application of a flame for 10 seconds at the fingertip.

### Available in sizes:



Recommended size	9	10	11
Circumference in cm	21	24	26

Measured with the hand closed.